

Dickentoleranzen von Verbundwerkstoffplatten

Table of rigid laminates thickness tolerances

	Dickentoleranz / Tolerance of thickness [mm]				
Platten- dicke ¹⁾ Sheet Thickness [mm]	HP 2061 PFCP 201 HP 2061.5 PFCP 202	HGW 2082 PFCC 201 HGW 2082.5 PFCC 202	HGW 2083 PFCC 203	HGW 2372 EPGC 201 HGW 2372.1 EPGC 202 / FR 4 HGW 2372.4 EPGC 203	HGW 2370.4 EPGC 205
0,4	± 0,07	-	-	± 0,10	-
0,5	± 0,08	-	± 0,13	± 0,12	-
0,6	± 0,09	-	± 0,14	± 0,13	-
0,8	± 0,10	± 0,19	± 0,15	± 0,16	-
1,0	± 0,12	± 0,20	± 0,16	± 0,18	-
1,2	± 0,14	± 0,22	± 0,17	± 0,20	-
1,5	± 0,15	± 0,24	± 0,19	± 0,24	-
2,0	± 0,19	± 0,26	± 0,21	± 0,28	± 0,40
2,5	± 0,22	± 0,29	± 0,24	± 0,33	-
3,0	± 0,25	± 0,31	± 0,26	± 0,37	± 0,50
4,0	± 0,30	± 0,36	± 0,32	± 0,45	± 0,60
5,0	± 0,34	± 0,42	± 0,36	± 0,52	± 0,70
6,0	± 0,37	± 0,46	± 0,40	± 0,60	± 0,80
8,0	± 0,47	± 0,55	± 0,49	± 0,72	± 1,00
10,0	± 0,55	± 0,63	± 0,56	± 0,82	± 1,00
12,0	± 0,62	± 0,70	± 0,64	± 0,94	+2,0 / -1,0
14,0	± 0,69	± 0,78	± 0,70	± 1,02	+2,0 / -1,0
16,0	± 0,75	± 0,85	± 0,76	± 1,12	+2,0 / -1,0
20,0	± 0,86	± 0,95	± 0,87	± 1,30	+2,0 / -1,0
25,0	± 1,00	± 1,10	± 1,02	± 1,50	+2,0 / -1,0
30,0	± 1,15	+2,5 / -0	+2,5 / -0	± 1,70	+4,0 / -0
35,0	± 1,25	+2,5 / -0	+2,5 / -0	± 1,95	+4,0 / -0
40,0	± 1,35	+2,5 / -0	+2,5 / -0	± 2,10	+4,0 / -0
45,0	± 1,45	+3,0 / -0	+3,0 / -0	± 2,30	+4,0 / -0
50,0	± 1,55	+3,0 / -0	+3,0 / -0	± 2,45	+5,0 / -0
60,0	-	+3,0 / -0	+3,0 / -0	-	+5,0 / -0
70,0	-	+3,5 / -0	+3,5 / -0	-	+5,0 / -0
80,0	-	+4,0 / -0	+4,0 / -0	-	+6,0 / -0
90,0	-	+5,0 / -0	+5,0 / -0	-	+6,0 / -0
100,0	-	+5,0 / -0	+5,0 / -0	-	+6,0 / -0

¹⁾ Für Zwischendicken, welche nicht in der Tabelle angeführt sind, gilt die Dickentoleranz der nachsthöheren Dicke!
For sheets, where the thickness ist not specified in the above table, the tolerance of the next bigger thickness ist valid!